## IN THE CLAIMS

The following is a listing of the claims in the present application with claims 1, 3, 4 and 8 shown as amended, claims 2 and 5-7 as deleted, and new claim 10 added:

## **Listing of Claims:**

- (Currently Amended) A method for producing DME <u>dimethylether</u>

  (DME), which comprises the steps of:
- (i) introducing a feed gas mixture containing hydrogen and CO to a DME synthesis reactor, wherein the feed gas mixture is reacted in the presence of a methanol synthesis catalyst and an acid catalyst for the dehydration of methanol, to provide a crude product stream containing DME and CO<sub>2</sub>;
- (ii) separating the crude product stream into a CO<sub>2</sub> rich stream and a DME rich stream;
- (iii) introducing the CO<sub>2</sub> rich stream to a reverse water gas shift (RWGS) reactor wherein it is reacted with hydrogen <u>separately introduced</u> in the presence of a catalyst an oxide catalyst to provide a CO rich stream, while recovering the DME rich stream as a product, the oxide catalyst being ZnO supported on or coprecipitated with an oxide selected from Al<sub>2</sub>O<sub>3</sub>, ZrO<sub>2</sub>, MgO, SiO<sub>2</sub>

and a mixture thereof, and the reaction in the reverse water gas reactor being carried out at a temperature ranging from 500 to 900 °C; and

- (iv) recycling the CO rich stream to step (i).
- 2. (Cancelled).
- 3. (Currently Amended) The method of claim-2 claim 1, wherein the exide catalyst is ZnO supported on or coprecipitated with an exide selected from Cr<sub>2</sub>O<sub>3</sub>, Al<sub>2</sub>O<sub>3</sub>, ZrO<sub>2</sub>, MgO, MnO, SiO<sub>2</sub> and a mixture thereof, the content of ZnO being in the ZnO catalyst ranges from 10 to 90 % by weight based on the total weight of the catalyst.
- 4. (Currently Amended) The method of claim 3 claim 1, wherein the ZnO catalyst further comprises an oxide of Cu or Mn in an amount of 0.01 to 60 % by weight based on the total weight of the catalyst.
  - 5.-7. (Cancelled).
- 8. (Currently Amended) The method of claim 2, wherein A method for producing dimethylether (DME), which comprises the steps of:
- (i) introducing a feed gas mixture containing hydrogen and CO to a

  DME synthesis reactor, wherein the feed gas mixture is reacted in the presence of a

methanol synthesis catalyst and an acid catalyst for the dehydration of methanol, to provide a crude product stream containing DME and CO<sub>2</sub>;

- (ii) separating the crude product stream into a CO<sub>2</sub> rich stream and a DME rich stream;
- (iii) introducing the CO<sub>2</sub> rich stream to a reverse water gas shift (RWGS) reactor wherein it is reacted with hydrogen separately introduced in the presence of an oxide catalyst to provide a CO rich stream, while recovering the DME rich stream as a product, the oxide catalyst is being NiO supported on or coprecipitated with an oxide selected from Cr<sub>2</sub>O<sub>3</sub>, Al<sub>2</sub>O<sub>3</sub>, ZrO<sub>2</sub>, MgO, SiO<sub>2</sub> and a mixture thereof, the content of NiO being 1 to 20 % by weight, preferably 1 to 10 % by weight based on the total weight of the catalyst and the reaction in the reverse water gas reactor being carried out at a temperature ranging from 700 to 900 °C; and
  - (iv) recycling the CO rich stream to step (i).
- 9. (Original) The method of claim 1, wherein the molar ratio of hydrogen and CO in step (iv) is controlled to  $0.9 \sim 1.5$ : 1.
- 10. (New) The method of claim 8, wherein the content of NiO in the NiO catalyst ranges from 1 to 20 % by weight based on the total weight of the catalyst.